

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
30 June 2005 (30.06.2005)

PCT

(10) International Publication Number  
WO 2005/059044 A1

- (51) International Patent Classification<sup>7</sup>: D06N 7/00, H05F 3/02 C09D 5/24
- (21) International Application Number: PCT/EP2004/053091
- (22) International Filing Date: 25 November 2004 (25.11.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 03293199.0 17 December 2003 (17.12.2003) EP
- (71) Applicant (for all designated States except US): TAR-KETT SAS [FR/FR]; 2, rue de l'Égalité, F-92000 Nanterre (FR).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): STOKKI, Anders [SE/SE]; Götgatan 52, S-37232 Ronneby (SE). KARLSSON, Roland [SE/SE]; Hellmansväg, S-37274 Listerby (SE).
- (74) Agents: KHN, Pierre et al.; Office Ernest T. Freylinger S.A., B.P. 48, L-8001 Strassen (LU).
- (84) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ELECTRICALLY CONDUCTIVE FLOOR COVERINGS

(57) Abstract: A surface covering comprising a substrate and a top coating characterised in that the top coating comprises particles with a conductive coating having a mean size between 0.1 and 50 µm.

## ELECTRICALLY CONDUCTIVE FLOOR COVERINGS

### *Field of the Invention*

The invention relates to an electrically conductive floor covering.

### *Description of the-Related Art*

Static charges, which are produced by walking or travelling on plastic floor coverings, particularly at low atmospheric humidity, represent a serious problem, particularly for sensitive electronic components. The electronic components may be damaged or their function may be impaired by electrostatic discharges. Furthermore, in areas in which easily flammable materials are worked with, there is the danger that these materials will be ignited by spark-over in the event of static discharges. The avoidance of static charges is particularly important in surroundings which are air-conditioned and therefore have a low atmospheric humidity, such as computer centers, manufacturing facilities for electronic components and electronic devices, radiological facilities, operating rooms, and other areas in which care is taken to provide an atmosphere low in dust and particles.

The floor coverings typically used, for example those based on polyvinyl chloride or rubber mixtures, are insulators. They may be made conductive if conductive fillers or antistatic agents are mixed in. However, a relatively large quantity, typically between 30 and 50 volume-percent of a conductive filler, must be used to achieve a sufficient conductivity. Metallic materials, conductive carbon black, or graphite are used in particular as conductive fillers, but the use of the necessary quantities results in black or gray products. If antistatic agents are used, there is the disadvantage that these materials react very strongly to changes in atmospheric humidity and their effectiveness is therefore strongly dependent on the environmental conditions.

A method for producing highly compressed, conductive covering material from thermoplastic plastics is known from European Patent A 869 217, in which particles of the thermoplastic plastic, which are provided with a coating

containing a conductive substance, are compressed under elevated temperature and high pressure into a block with conductive paths and subsequently split transversely to the direction of the conductive paths into slabs of the desired thickness, with these slabs having conductive paths in the direction of their thickness. In this way, light-colored, conductive floor coverings made of thermoplastic plastic are obtained.

Polyurethane (PU) and other top coatings such as PU acrylates, epoxy acrylates, polyester acrylates, polyether acrylates, silicone acrylates etc are widely used as surface reinforcement on plastic floorings, for residential use as well as for commercial use. These top coatings make the surface of the floor covering smoother, decrease the friction and because of that improve the cleaning and maintenance properties.

One disadvantage with the existing top coatings is their electrical insulation properties that make them unsuitable for conductive homogeneous floorings.

Conductive floorings should have an electrical resistance between 0,05 and 1,0 M $\Omega$  during the entire product lifetime. To reach this goal, the top coating should not have any or very low influence on the total conductivity of the flooring. The conductivity of the flooring should be determined by the amount and quality of conductive material in the substrate, for example by the carbon black (black spots) integrated into the substrate.

For a conductive floor covering the electrical resistance according to EN 1081 will increase from approx. 0,05-0,1 M $\Omega$  to more than 100 M $\Omega$  when a traditional top coating is applied. The height of the increase depends on thickness, the nature and grade of the top coating used.

The use of chemical additives to lower the electrical resistance is well known, but is not suitable for floorings because the resulting top coatings show a low stain resistance, a risk for migration of the additives in some cases and because the conductivity obtained is not stable in time. Often these chemicals also decrease the transparency and/or give a colour to the top coating.

Mineral materials or conductive pigments can also be used to lower the electrical resistance, but they have generally a colouring effect on the coating.

### **SUMMARY OF THE INVENTION**

In accordance with the present invention, a surface covering comprising a substrate and a surface or top coating is provided for conductive flooring with a top coating exhibiting improved cleaning and maintenance properties as well as an good transparency.

Accordingly the invention provides a new and improved surface covering comprising a substrate and a top coating characterised in that the top coating comprises particles with a conductive coating having a mean particle size (in numbers) between 0.1 and 50  $\mu\text{m}$ .

The conductive flooring with a top coating according to the invention exhibits improved cleaning and maintenance properties as well as an increased transparency. Furthermore the conductivity of the flooring remains constant during its entire lifetime.

According to a preferred embodiment, the particles are substantially spherical. Such spherical particles are more easily mixed with the top coating before the application of said top coating to the substrate.

The particles preferably comprise a coating of silver, aluminium, copper, nickel, gold or an alloy thereof with another metals. Metal-coated spherical beads are especially preferred. Such a metal coating gives very good performances and allows to effectively lead any charges accumulating in the top coating down the substrate through which they are then lead to the ground.

The particles or the metal-coated spherical beads have a dry bulk resistivity of advantageously between 0.0001 and 0.01 Ohms/cm. Very good results are achieved with metal-coated spherical beads having a dry bulk resistivity of about 0.001 Ohms/cm.

The top coating comprises – in a preferred embodiment – between 0.01 and

10% w/w of particles based on the weight of the top coating. The optimal ratio depends mainly on the type and on the thickness of top coating material used.

The top coating comprises preferably a PU-dispersion (like Neovez R988 of Neokesins), a PU-solution, a 2-components PU, a PU acrylate (like Aqualux 1420-8500 from Teknos A/S), an epoxy acrylate, a polyester acrylate, a polyether acrylate, a silicone acrylate or a mixture thereof.

The coating comprises an urethane derived polymer preferably polyurethane and most preferably a water based UV-curable PU-acrylate dispersion with a dry content of between 5% and 80% w/w preferably 20 and 60 % w/w. Such top coatings are widely used in the art for applications where an electrical conductivity is not required.

The top coating normally has a thickness of between 0,5  $\mu\text{m}$  to 100  $\mu\text{m}$ .

The top coating may be applied by any known technique like roller coating, reverse and inreverse, spraying, curtain, screen etc.

Of course, the size of the particles with a conductive coating thickness depends on the thickness of the top coating. As a general rule, the mean size of the particles should be not be more than about half of the thickness of the top coating.

The above described top coating may be used on any a conductive and antistatic flooring, preferably on a PVC based flooring with vertical conductive channels, containing carbon black. Such a product is commercially available from the Tarkett AB under the trademark TORO EL. Polyolefin or rubber based floors may also be used.

#### **DETAILED DESCRIPTION OF A PREFERRED EMBODIMENTS**

The present invention will be described in more detail in the following with reference to the example

Example1

In order to produce a conductive flooring the following materials were used:

- 5        1) Conductive silver glass spheres (CSGS 10 A, available from Proges-  
sive Fillers Int'l Inc. of Tennessee, USA) having a mean particle size of 10  $\mu\text{m}$ , a  
pure silver plating of 12% and a dry bulk resistivity of 0.001 Ohms/cm

2) Top coat: Aqualux™ from Teknos A/S Denmark, a water based  
UV-curable PU-acrylate dispersion with a dry content of approx. 40 %.

- 10       3) Plastic flooring of PVC (Toro EL available from Tarkett AB Swe-  
den) with "vertical conductive channels" containing carbon black.

About 1 % w/w of CSGS 10A were mixed in the above mentioned PU-  
acrylate dispersion and the conductive flooring were coated with approx 20 g/m<sup>2</sup>  
in a roller coating station.

The "film" thickness of the top coating after drying was about 8  $\mu\text{m}$ .

- 15       Two control samples were used to compare the results one without any  
top coating and an other one with the same top coating but without any conductive  
particles.

20       Since only approx. 1 % of CSGS 10A particles were used the top coat-  
ing is transparent. The CSGS 10A particles give no or very little visible change of  
the surface. The rather low content of spheres implies also that the top coat only is  
conductive in the vertical direction from the surface to the conductive substrate  
and not in the horizontal direction.

The properties of the flooring were determined according to the follow-  
ing methods

- 25       1) European Standard EN 1081 (January 1998) : Resilient floor cov-  
erings-Determination of the electrical resistance.

2) ESD association standard (ANSI/ESDS7.1-1994) )

It was found that the electrical resistance of the conductive flooring

(Toro EL) without top coat was between 0,03- 0,1 M $\Omega$  , whereas the electrical resistance of the conductive flooring (Toro EL) with PU coating without CSGS was >500 M $\Omega$ . The electrical resistance of conductive flooring (Toro EL) with conductive PU according to the invention was 0,05- 0,2 M $\Omega$ .

- 5           No colour change was noticed using the above concentration of particles, no dependency on air humidity and a very high vertical conductivity through the top coating according to the invention to the conductive parts (carbon black) in the substrate. This top coating does not increase the electrical resistance of the flooring significantly. The resistance of the substrate beneath the PU top coat  
10 determines the flooring conductivity. Since a "normal" amount of PU was used, the flooring cleaning properties were very much improved compared to the reference without PU.

**Claims**

1. A surface covering comprising a substrate and a top coating characterised in that the top coating comprises particles with a conductive coating having a mean size between 0.1 and 50  $\mu\text{m}$ .
- 5 2. The surface covering according to claim 1, wherein the particles are substantially spherical.
3. The surface covering according to claim 1 or 2, wherein the particles comprise a coating of silver, aluminum, copper, nickel, gold or an alloy thereof with another metals.
- 10 4. The surface covering according to any of the preceding claims, wherein the particles have a dry bulk resistivity of between 0.0001 and 0.01 Ohms/cm.
5. The surface covering according to any of the preceding claims, wherein the top coating comprises between 0.01 and 10% w/w of particles based on the weight of the top coating.
- 15 6. The surface covering according to any of the preceding claims, wherein the top coating comprises a PU-dispersion, a PU-solution, a 2-components PU, a PU acrylate, an epoxy acrylate, a polyester acrylate, a polyether acrylate, a silicone acrylate or a mixture thereof
7. The surface covering of claim 5, wherein the coating comprises an urethane  
20 derived polymer preferably polyurethane.
8. The surface covering of claim 5, wherein the coating comprises a water based UV-curable PU-acrylate dispersion with a dry content of between 5 % and 80% w/w , preferably between 20 and 60 % w/w.

9. The surface covering according to any of the preceding claims, wherein the top coating has a thickness of between 0,5  $\mu\text{m}$  to 100  $\mu\text{m}$
10. The surface covering according to any of the preceding claims, wherein the substrate is a conductive and antistatic flooring.
- 5 11. The surface covering according to any of the preceding claims, wherein the substrate is a PVC, polyolefin or rubber based flooring with vertical conductive channels.